

TECHNICAL DATA SHEET

OLD MASTERS[®] GRAINING BASE

AVAILABLE SIZES: Pint (08), Quart (04) and Gallon (01)

PRODUCT CODES: 202 Driftwood 213 Pine
203 Walnut 214 Mahogany
212 Maple

PRODUCT DESCRIPTION: Old Masters[®] Graining Base is a high quality, oil-based paint. This product can be used alone or under Wiping Stain to achieve a wide variety of distinctive decorating effects. When used as a basecoat for woodgraining, this product simulates both the texture and color of bare or unfinished wood. Graining Base can be used on any paintable, interior surface and provides a base coat for woodgraining. Woodgraining can be achieved on new wood, previously finished surfaces, cabinets, furniture and metal doors, without stripping previous finishes. This product will not raise wood

SURFACE PREPARATION: All surfaces must be clean, dry and free from dirt, wax, grease, glue and other contaminants or adhesion will be affected.

New or Bare Wood: Sand surface thoroughly. Remove dust with a lint free rag or tack rag.

Previously Finished Surfaces: Previous finish does not need to be removed if in sound condition. If in poor condition, remove finish and sand smooth. Remove dust.

Metal or High Gloss Surfaces: Remove gloss by sanding to roughen surface. Ensure adhesion, then remove all dust particles with a tack rag.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION: Stir thoroughly before and during use. Apply with a good quality, natural bristle brush or spray application. On metal surfaces, such as doors, apply Graining Base in the direction of the intended woodgrain. Should a second coat be desired, allow first coat to dry for 24 hours. Once thoroughly dry, sand surface lightly, then recoat. Also allow 24 hours drying time prior to applying Wiping Stain to achieve a woodgrain effect.

THINNING: Do not thin. Use as packaged.

COVERAGE: Approximately 100 square feet per quart.

DRYING TIME: Approximately 3 to 6 hours, depending on humidity, temperature and use of product (as a stain or glaze). It can be topcoated after 12 hours if glaze is thoroughly dry.

CLEAN UP: Using a cleaning solvent, such as paint thinner or mineral spirits, is recommended for cleanup. The use of paint thinners or mineral spirits may violate VOC compliancy in your area. Check with your local government agencies to ensure proper compliancy.

To avoid spontaneous combustion during temporary storage, soak soiled rags and waste immediately after use in a water-filled, closed metal container.

MAX VOC: 380 grams/liter (3.2 lbs/gal)

TECHNICAL DATA SHEET

OLD MASTERS[®] GRAINING BASE

TECHNICAL DATA

GLOSS:	20-25 @ 60°	WEIGHT PER GALLON:	10.6-11.0 lbs.
SOLIDS BY WEIGHT:	70-72%	FLASH POINT:	102°F Tag Closed Cup
SOLIDS BY VOLUME:	50-53%	VISCOSITY AT 77 °:	72 - 74 Krebs Units
V.O.C.:	380 grams/liter	AVERAGE DRY TIME @ 70°F AND 50% R.H.:	Approximately 8 to 10 hours
THEORETICAL COVERAGE @ Mil DFT:	815-840 sq. ft. per gal	RECOMMENDED THINNER:	Do not thin. Used as packaged.
COVERAGE @ RECOMMENDED DFT	400-450 sq. ft.		
RECOMMENDED DFT PER COAT:	1 1/2 mil/coat DFT		

Limited Warranty Since Old Masters[®] does not control the application of its products, nor is the condition of the surface to which they are applied, a Limited Warranty provided. If the products do not perform as specified, for whatever reason, Old Masters[®] liability will under no circumstances exceed the replacement of the product.