

TECHNICAL DATA SHEET

OLD MASTERS[®] PENETRATING SEALER

AVAILABLE SIZES: Quart (04) and Gallon (01)

PRODUCT CODES: 92604
92601

PRODUCT DESCRIPTION: Old Masters[®] Penetrating Sealer is a clear, penetrating oil formulated with natural Tung oil to protect and seal a variety of surfaces including wood, masonry and concrete. This product seals surfaces to resist weather, mold and mildew. Suitable for both interior and exterior applications, this product can be used as a seal coat under clear finishes or paint. On wood surfaces, this product seals out moisture to enhance the life and natural appearance of wood while preventing staining and checking. On masonry and concrete it will produce a moisture seal that reduces concrete dusting, staining and efflorescence of masonry and brick surfaces. Sealer also hardens masonry and natural rock surfaces and reduces

SURFACE PREPARATION: All surfaces must be clean, dry and free from dirt, wax, grease, glue and other contaminants or penetration will be affected. Stir thoroughly before and during application.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION: Wood Surfaces

1. Sand bare wood if necessary and remove dust.
2. Apply two or more liberal coats of Penetrating Sealer, depending on porosity of the wood, at 10 to 15 minute intervals.
3. Allow final coat to stand 10 minutes, then wipe off excess sealer.
4. Apply desired finish coat after surface has dried 12 to 18 hours.

Masonry Surfaces

1. Remove all loose particles by wire brushing. Excessive stains or grease-spotted surfaces should be thoroughly cleaned before applying sealer.
2. Neutralize new concrete, masonry, stucco, or brick prior to application of sealer.
3. Apply liberal coats as required. Allow 10 to 15 minutes for penetration, and then remove excess material.

Helpful Hint: Penetrating Sealer will amber slightly; do not use on white or light colored masonry surfaces.

THINNING: Do not thin. Use as packaged.

COVERAGE: Approximately 230 to 470 square feet per gallon. Coverage will vary significantly depending on application method and condition of wood.

TECHNICAL DATA SHEET

OLD MASTERS[®] PENETRATING SEALER

DRYING TIME: Penetrating Sealer will dry in 12 to 16 hours. Allow 12 to 16 hours drying time prior to topcoating. High humidity, low temperature or lack of air movement will extend drying time.

CLEAN UP: Using a cleaning solvent, such as paint thinner or mineral spirits, is recommended for cleanup. The use of paint thinners or mineral spirits may violate VOC compliancy in your area. Check with your local government agencies to ensure proper compliancy.

To avoid spontaneous combustion during temporary storage, soak soiled rags and waste immediately after use in a water-filled, closed metal container.

MAX VOC: 200 grams/liter (7.6 lbs/gal)

TECHNICAL DATA

GLOSS:	Not applicable	WEIGHT PER GALLON:	7.55 lbs
SOLIDS BY WEIGHT:	77.9%	FLASH POINT:	102°F Tag Closed Cup
SOLIDS BY VOLUME:	74.8%	VISCOSITY AT 77 °:	16-18 sec. #2 Zahn
V.O.C.:	200 grams/liter	AVERAGE DRY TIME @ 70°F AND 50% R.H.:	Approximately 10 to 12 hours
THEORETICAL COVERAGE @ Mil DFT:	Not applicable	VEHICLE:	Alkyd/Oil blend
COVERAGE @ RECOMMENDED DFT	Not applicable	RECOMMENDED THINNER:	Do not thin. Use as packaged.
RECOMMENDED DFT PER COAT:	Not applicable		

Limited Warranty Since Old Masters[®] does not control the application of its products, nor is the condition of the surface to which they are applied, a Limited Warranty provided. If the products do not perform as specified, for whatever reason, Old Masters[®] liability will under no circumstances exceed the replacement of the product.